## **Technical Data Sheet**



Peter Kwasny GmbH, Heilbronner Str. 96 74831 Gundelsheim / Deutschland Telefon: +496269 95-0, Fax: +496269 95-80 www.spraymax.com / www.kwasny.com / info@kwasny.de

# SprayMax® 2K Clear coat matt 400 ml Art. Nr. 680065



### **Product**

**Description / Purpose** 

**Properties** 

**Material base** 

**Gloss level** 

**VOC Value (EU)** 

2K clear coat with very high chemical, gasoline, and weathering resistance for high-quality and longterm sealing of repair paint jobs and new paint jobs on cars and motorcycles.

- · Maximum resistance to abrasion and scratching
- · Very smooth flow
- Very good polish ability
- No colour deviation
- · Outstanding painting surface
- · Suitable even at higher ambient temperatures
- Ideally suited for large surfaces

Two-component acrylic resins

Activator: aliphatic isocyanates

matt

16+ / -2 gloss units at 85° measuring angle

648 g/l

## **Substrate**

Solvent and waterborne base coat systems, old paint coats dried according to manufacturer's instructions (cleaned and sanded).



## **Processing**

**Protection measures** 



Wear personal protection equipment. (respiratory mask/gloves/goggles)

For more information, see safety data sheet.

Shake



Before activating, shake can thoroughly for 2 minutes from when the mixing balls are heard.

Place red button



Remove the red button from the cap. Turn the can by 180° and fit the button onto the pin.

**Press red button** 



Turn the can upside down and place on a firm surface. Press the red button with the palm of your hand until it clicks into place.

**Shake** 



After activating, shake can again thoroughly for 2 minutes, again from when the mixing balls are heard.

Spray to test



After shaking the can, test spray and check compatibility with the surface and the colour.

**Spraying distance** 



15 cm - 20 cm

**Spray passes** 



Dry film thickness 40 μm (approx. 1 - 2 spray coats)

Flash-off time



Flash time: approx. 10 - 15 min between each spray coat

**Processing conditions** 



Optimum application at 18° C - 25° C and a relative humidity from 40 - 60 %.



#### Coverage



approx.  $0.5 - 0.75 \text{ m}^2$  at  $30 - 50 \mu \text{m}$  dry film thickness

#### **Drying**



TG1 dust dry: 12 min
TG3 dry to touch: 80 min

The stated values refer to the above mentioned processing conditions. The level of dryness is determined pursuant to DIN 53150.



IR- drying possible,Observe equipment description

#### Pot life



Approx. 48 h at 20 °C room temperature and a relative humidity of approx. 40 - 50 %. The processing time depends on the ambient temperature. Higher temperatures reduce the pot life, lower temperatures will prolong it.

#### **Finish**



After painting, turn the can upside down and spray the valve until empty.

## **Additional Information**

#### **Shelf Life**



36 months (not activated)

The usage period refers to an unused can that is stored correctly at a temperature of 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.



#### **Disposal**



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

#### Note

For professional use only.

Identification, see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.